

---

## TUBIJET® DU 02

<b>Character</b>	Primer for digital reactive printing on textiles to improve sharpness.
<b>Chemical Composition</b>	Anionic, water soluble polymer
<b>Appearance</b>	Colourless to slightly yellowish liquid
<b>Ionic Character</b>	Anionic
<b>pH Value</b>	5,0 – 8,0
<b>Solubility</b>	TUBIJET® DU 02 is miscible with water.
<b>Stabilities</b>	Can be used together with non-ionic or anionic products. Cationic products may lead to precipitation.
<b>Storage</b>	Stir before removal. Store in a cool and dry place in tightly closed, original containers. Opened containers must be closed again tightly. We recommend not exceeding a storage time of 12 months.

---

The above given values are product describing data. Please consult the 'delivery specification' for binding product specifications. Further data about product properties, toxicological, ecological data as well as data relevant to safety can be found in the safety data sheet.

### Properties

TUBIJET® DU 02 is a universal applicable product for preparing textiles for digital reactive printing. The product acts as an anti migrant to the water based printing inks. It can be used on cotton, viscose and modal fibers, offering the following advantages:

- Anti-migrant
- Homogenous prints
- Dark and brilliant colors
- Easily washed out
- Soft hand even with viscose
- Solvent-free

TUBIJET® DU 02 can also be used in digital disperse printing to improve print sharpness. For further information, please contact our Technical Service.

® = registered trademark

## Technical Guidelines

### Application

Method: Padding

Diluting instructions: The product can be diluted with cold water to any ratio. Be sure to mix well. In order to prevent foaming, the sequence given in the table should be followed when preparing the liquor.

Cleaning instructions: Before use, we recommend rinsing all vessels and especially the pumps with water in order to prevent any contamination with cationic substances which could cause precipitations.

### Process

- Primer application before printing by foulard

Product	Recipe 1
RAPIDOPRINT® SC 10	1-2 g/l
RAPIDOPRINT® XR GRANULAT	10 g/l
TUBIJET® DU 02	125 g/l
Urea*	100 g/l
Bicarbonate	40 g/l
Soda	5 g/l

\*For viscose we recommend 200 g/l urea

Pick-Up: 70 – 100 %  
Drying: 100 – 110 °C 2 min

- Digital printing

- Steaming 102 °C saturated steam 8 – 12 min (CO), 10 – 15 min (CV)

- Washing

For the introduction into the continuous washing machine we recommend 2-3 g/l COTOBLANC STM (30 °C). In the other baths (60, 98 °C), which are run in countercurrent, we recommend 2-4 g/l COTOBLANC STM. Subsequently, rinse with soft water (40 °C) and acidify (30 °C).

**We reserve the right to modify the product and technical leaflet. Our department for applied technique is always at your service for further information and advice.**

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

**Edition: October 2022**

**CHT Germany GmbH**

**Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany**

**Telephone: +49 7071 154-0, Fax: +49 7071 154-290, Email: info@cht.com, Homepage: www.cht.com**