
TUT TX 145 1 P

Characterization	Adhesive for paper lamination industry, suitable to use in high speed machines
Chemical Structure	Phthalate free, vinyl acetate based homopolymer
Supplied Form	White viscous liquid
Ionic character	Anionic
pH Value	4.0 – 5.0
Viscosity at 20 °C	1500 – 2500 cp
Storage	With a proper storage condition at 5 - 40°C in closed original containers, the product holds for at least 12 months.

Properties

TUT TX 145 1 P is free of phthalate group which is restricted according to several international standards.

TUT TX 145 1 P forms clear and elastic films. TUT TX 145 1 P is suitable to use in all kind of serial packaging machines by having well adjusted viscosity and drying properties. Due to the change that may occur in viscosity, it is necessary to pay attention to the ambient temperature (room temperature).

Application technique

Diluting instructions

TUT TX 145 1 P can be diluted with water by mixing under the ratio of 5 %.

Application fields

TUT TX 145 1 P can be used in lamination processes in the manufacturing process of cardboard, corrugated cardboard, book binding papers.

The changes that may occur in the viscosity due to temperature need to pay attention. It is recommended to control the ambient temperature while working with the product.

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: July 2024

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, homepage: www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: :+90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com