
TUT T 240 GOLD P

Characterization

Adhesive for wood applications

Chemical Structure

Phthalate-free polyvinylacetate homopolymer

Supplied Form

White viscous liquid

pH Value (10 %)

6.0 – 8.0

Ionic Character

Anionic

Viscosity at 20°C

16000 – 22000 cps

Storage

TUT T 240 GOLD P can be stored for 12 months in closed original containers between 5 and 40°C.

Properties

TUT T 240 GOLD P does not contain the phthalate groups which are restricted in many international standards.

TUT T 240 GOLD P is generally used for wood, solid wood assembling, chipboard, MDF veneering and parquet bonding applications. Product can be applied on surface and then pressed. TUT T 240 GOLD P forms a strong, high-quality film.

Application

Diluting Instructions

TUT T 240 GOLD P can be diluted with water at any ratio.

Recommendation for Use

The surface of the material has to be smooth and dry.

We recommend to stir the product before use and close containers after use.

TUT T 240 GOLD P can be applied by brush, roller, spatula or spray techniques.

Ambient temperature should be over 15°C.

Open time: 3 – 5 min after application

Pressing time: 10 – 15 min at room temperature

Drying time: 0.5 – 2 hours at room temperature

Pressure: 10 – 11 N/mm²

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Version: August, 2024

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, **Fax:** 07071/154-290, **Email:** info@cht.com, **homepage:** www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: :+90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com