
TUBIJET® SHARP R 104

Character	Primer for digital reactive printing on textiles to improve homogeneity.
Chemical Composition	Modified, water-soluble polyacrylamide
Appearance	Light opal gel
Ionic Character	Nonionic
pH Value	5,0 – 8,0
Solubility	TUBIJET® SHARP R 104 is miscible with water.
Stabilities	Can be used together with non-ionic, anionic or cationic products.
Storage	Stir before removal. Store in a cool and dry place in tightly closed, original containers. Opened containers must be closed again tightly. We recommend not exceeding a storage time of 12 months.

The above given values are product describing data. Please consult the 'delivery specification' for binding product specifications. Further data about product properties, toxicological, ecological data as well as data relevant to safety can be found in the safety data sheet.

Properties

TUBIJET® SHARP R 104 is a universal applicable product for preparing textiles for digital reactive printing. Due to its gel-forming property, the product ensures an even and optimum distribution of the ink. This results in both a homogeneous print image and improved penetration of the ink into the textile. It offers the following advantages especially on hairy or coarse cotton fibers:

- Homogenous prints
- Anti-migrant
- Solvent-free

Technical Guidelines

Application

Method: Padding

Diluting instructions: The product can be diluted with cold water to any ratio. Be sure to mix well. In order to prevent foaming, the sequence given in the table should be followed when preparing the liquor.

Cleaning instructions: Before use, we recommend rinsing all vessels and especially the pumps with water in order to prevent any contamination with cationic substances which could cause precipitations.

Process

- Primer application before printing by foulard

Product	Recipe 1
RAPIDOPRINT® SC 10	1 - 2 g/l
RAPIDOPRINT® XR GRANULAT	10 g/l
TUBIJET® SHARP R 104	50 g/l
TUBIJET® DU 02	50 g/l
Urea*	100 g/l
Bicarbonate	40 g/l
Soda	5 g/l

*For viscose we recommend 200 g/l urea

Pick-Up: 100 – 150 %
Drying: 100 – 110 °C 2 min

- Digital printing

- Steaming 102 °C saturated steam 8 – 12 min (CO), 10 – 15 min (CV)

- Washing

For the introduction into the continuous washing machine we recommend 2 - 3 g/l COTOBLANC STM (30 °C). In the other baths (60 °C, 98 °C), which are run in countercurrent, we recommend 2 - 4 g/l COTOBLANC STM. Subsequently, rinse with soft water (40 °C) and acidify (30 °C).

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: October, 2022

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, homepage: www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: :+90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com