

---

## AVISTAT AZ NEW

<b>Character</b>	Antistatic agent
<b>Chemical character</b>	Fatty acid condensation product
<b>Appearance</b>	Light beige, pink beige liquid emulsion
<b>Ionic character</b>	Cationic
<b>pH-value of a 10 % solution</b>	2.0 – 3.2
<b>Specific weight at 20 °C</b>	~ 0.98
<b>Stabilities</b>	<p>AVISTAT AZ NEW has good stability to the usually applied amounts of chemicals and to hard water.</p> <p>The product is sensitive to frost to a limited extent; changes occurring at low temperatures are reversible on warming and after good stirring.</p>
<b>Storage</b>	If stored properly in closed original containers, AVISTAT AZ NEW will hold for at least 12 months.

---

## Properties

AVISTAT AZ NEW is an efficient antistatic agent with slight softening properties. The resulting handle is full and voluminous.

AVISTAT AZ NEW gives excellent antistatic effects on synthetic fibres.

AVISTAT AZ NEW is fast to sublimation and not steam volatile. It does not deposit in the drying aggregates and therefore soiling is not to be expected.

## Application technique

### Diluting instructions

AVISTAT AZ NEW can be mixed with cold water at any ratio.

### Application Fields

AVISTAT AZ NEW is suitable for all synthetic fibres. AVISTAT AZ NEW picks up substantively to the synthetic fibres. Therefore, industrial water ought to be adjusted with acetic acid if necessary when the product is applied by means of the exhaust process. At pH of 5.0 - 6.0 AVISTAT AZ NEW shows the highest substantivity.

When working continuously on the padding mangle, there is no need for a pH correction as substantivity is not desired in such processes.

If heat-setting is to be carried out after the antistatic finish, the finishing effect may be slightly impaired as the product diffuses into the fibre, so that the surface efficiency decreases.

## Recipe proposals

### 1. Exhaust method

1.0 - 2.0 % AVISTAT AZ NEW o. w. f.

treat for 20 - 30 min. at about 40 - 50 °C  
adjust pH 5.0 – 6.0 with acetic acid

### 2. Padding method

5.0 - 10.0 g/l AVISTAT AZ NEW

The temperature of the padding liquor can be chosen from cold up to 50 °C.  
Drying is carried out under the usual conditions.

## Recommendation for Use

### Corduroy or plush

Due to the antistatic finish the fibre fly is prevented from adhering to the cloth when shearing, which is favourable for an even appearance of the goods. The following amounts may serve as a guideline:

1.0 - 2.0 % AVISTAT AZ NEW o. w. f.

### Preparation of high bulk yarns

Despite the fact that so far a smooth, full handle has been desired besides good antistatic properties, we can now observe the tendency that merely a very efficient antistatic agent is often demanded. In such cases we recommend applying AVISTAT AZ NEW. Usually

1.0 - 2.0 % AVISTAT AZ NEW o. w. f.  
0.5 - 1.0 ml/l acetic acid 30 %

are sufficient. Treat for approx. 20 min at 30 - 50 °C.

#### Knitted goods

Texturized polyamide articles are finished antistatically in the exhaust and padding method.

Exhaust process:

1.0 - 2.0 % AVISTAT AZ NEW o. w. f.

neutral or slightly acid, 20 min at 30 °C

Padding process:

10.0 - 30.0 g/l AVISTAT AZ NEW when processing dry-on-wet

temperature cold to lukewarm, neutral

**We reserve the right to modify the product and technical leaflet.**

**Our department for applied technique is always at your service for further information and advice.**

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

**Edition:** August, 2025

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: [info@cht.com](mailto:info@cht.com), homepage: [www.cht.com](http://www.cht.com)

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: :+90 212 886 79 13, Fax: +90 212 886 93 47,

Email: [info.turkey@cht.com](mailto:info.turkey@cht.com)