
TUT TX 145 2 P

Characterization	Adhesive with elastic film properties used for fast and strong paper bonding applications
Chemical Structure	Phthalate free, polyvinyl acetate homopolymer
Supplied Form	White low viscous liquid
Ionic character	Anionic
pH Value	4.0 – 5.0
Viscosity at 20 °C	800 – 1000 cps (RVT, spindle:2, 20 rpm)
Storage	With a proper storage conditions at 5 - 40°C in closed original containers, the product holds for at least 6 months.

Properties

TUT TX 145 2 P is free of phthalate group which is restricted according to several international standards.

TUT TX 145 2 P is suitable to use in all kind of serial packaging machines by having well adjusted viscosity and drying properties. The product forms clear and elastic films. Due to possible changes in viscosity, attention must be paid to ambient temperature (room temperatures).

Application technique

Diluting instructions

TUT TX 145 2 P can be diluted with water (not above 5 %) while stirring.

Application fields

TUT TX 145 2 P can be used in lamination processes in the manufacturing process of cardboard, corrugated cardboard, book binding papers and paper-to-paper box production.

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: August, 2024

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, homepage: www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: +90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com