
REWIN IN 105 S

Character	Cationic aftertreatment agent
Chemical Character	Polyammonium compound
Appearance	Yellow liquid
Ionic Character	Cationic
pH Value	5.5 – 6.5
Specific Weight at 20 °C	Approx. 1.1
Stabilities	<p>REWIN IN 105 S is stable to water hardness, electrolytes and the acid and caustic soda concentrations used in practice. It can be combined very well with non-ionic and cationic products. Together with anionic products precipitations may occur.</p> <p>The product is sensitive to frost to a certain extent. Changes occurring at low temperatures disappear when heating up the product and after thoroughly stirring it.</p>
Storage	If stored properly in closed original containers, it will hold for 12 months.

Properties

REWIN IN 105 S is a cationic aftertreatment agent used for improving the washing and wet fastnesses of dyeing and printing with reactive and direct dyestuffs on natural and regenerated cellulose fibres.

REWIN IN 105 S prevents poor wet fastness caused by dyestuff hydrolysis and thermal cracking in dyeing with reactive dyestuffs.

REWIN IN 105 S has the following advantages:

- Improvement of the washing fastnesses on washing with reactive and direct dyestuffs at 40 and 60°C,
- Improvement contact fastness such as water fastness and perspiration fastness,
- Slight influence on the light fastness and color shades depending on the dyestuff,
- No influence on fabric handle and therefore it has no adverse effect on sewability,
- No influence on rewettability
- Formaldehyde-free*

Application Technique

Diluting Instructions

REWIN IN 105 S can be diluted with cold water at any ratio.

Application Fields

The aftertreatment with REWIN IN 105 S is always done in a fresh bath. The recipes to be applied to the well-rinsed or well-soaped dyeings and printings are as follows;

Exhaust method:

2.0 – 3.0 % REWIN IN 105 S
pH 5.0 – 6.0
20 – 30 min. at 30 – 40 °C

Padding method:

5.0 – 20.0 g/l REWIN IN 105 S
pH 5.0 – 5.5
Pick up 80 – 100 %
Drying 120 - 140 °C

The application amount depends on the technical properties of the padding roller. Preliminary trials are recommended when necessary.

Stripping of dyeings aftertreated with REWIN IN 105 S:

If dyeings are to be redyed or levelled out, REWIN IN 105 S must be stripped or masked first.

The following stripping method has proven to be successful:

4.0 - 5.0 g/l CHT-DISPERGATOR SMS
pH 4.0 (with acetic acid 60 %)
20 - 30 min. at 98°C
then rinse thoroughly warm and cold

If the dyeing shall also be stripped, we recommend two-stage method:

1. Stripping of REWIN IN 105 S

4.0 - 5.0 g/l CHT-DISPERGATOR SMS
pH 4.0 (with acetic acid 60 %)
20 - 30 min. at 98°C

2. Stripping of the dyeing

x ml/l caustic soda
y g/l hydrosulphite or REDULIT F
3.0 - 5.0 g/l CHT-DISPERGATOR SMS
20 - 30 min. at 98°C
then rinse thoroughly warm and cold

* To us formaldehyde-free means that all recipe components neither contain nor release formaldehyde during production or processing.

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: May, 2024

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, homepage: www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: +90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com