

TUT T 540

Characterization	Water resistant wood glue
Chemical Structure	Polyvinyl acetate homopolymer
Supplied Form	White paste
pH Value	6.0 – 8.0
Specific Weight at 20 °C	Approx. 1.05 g/cm ³
Ionic Character	Anionic
Viscosity	14000 – 22000 cp
Storage	With a proper storage conditions at 5 - 40°C in closed original containers, the product holds for at least 12 months.

Properties

TUT T 540 is generally used for wood, chipboard, MDF veneering, parquet bonding, pressed laminate application, finger joint applications and solidifying works and as a skeleton glue applications. The product forms a clear film.

Application technique

The surface of the material has to be smooth and dry. The product must be stirred thoroughly before starting to use, and the container must be tightly closed after use.

TUT T 540 can be applied with a roller and spatula. The ambient temperature (room temperature) should not be below 15°C.

Application fields

TUT T 540 is used in bonding wood, chipboard, MDF veneering, parquet bonding, pressed laminate application and solidifying works and as a skeleton glue applications; It is applied by applying it to the surfaces with a brush, roller or cylinder and adhering. Product viscosity is ideal for finger joint applications.

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: July, 2024

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, homepage: www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: +90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com